



DOWLEX™ 2045G Polyethylene Resin

Overview

- Linear Low Density Polyethylene
- For heavy duty applications
- Complies with U.S. FDA 21 CFR 177.1520 (c) 3.2a.
- Consult the regulations for complete details.

DOWLEX™ 2045G Polyethylene Resin is designed for the production of a wide variety of industrial and consumer films. Films made from this resin exhibit a combination of excellent toughness and tear resistance. The product also delivers very good processability on conventional LLDPE machinery.

Additive

- Antiblock: No
- Slip: No
- Processing Aid: No

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.920 g/cm ³	0.920 g/cm ³	ASTM D792
Base Density	0.920 g/cm ³	0.920 g/cm ³	Dow Method ¹
Melt Index (190°C/2.16 kg)	1.0 g/10 min	1.0 g/10 min	ASTM D1238
Films	Nominal Value (English)	Nominal Value (SI)	Test Method
Film Thickness - Tested	1.0 mil	25 µm	
Film Puncture Energy	315 in-lb	35.6 J	Dow Method
Film Puncture Force	47.0 lbf	209 N	Dow Method
Film Puncture Resistance	14.0 ft-lb/in ³	1.16 J/cm ³	Dow Method
Film Toughness			ASTM D882
MD	1430 ft-lb/in ³	118 J/cm ³	
TD	1560 ft-lb/in ³	129 J/cm ³	
Secant Modulus			ASTM D882
1% Secant, MD	34400 psi	237 MPa	
2% Secant, MD	29800 psi	205 MPa	
1% Secant, TD	39900 psi	275 MPa	
2% Secant, TD	33600 psi	232 MPa	
Tensile Strength			ASTM D882
MD: Yield	1650 psi	11.3 MPa	
TD: Yield	1730 psi	11.9 MPa	
MD: Break	6870 psi	47.4 MPa	
TD: Break	5890 psi	40.6 MPa	
Tensile Elongation			ASTM D882
MD: Break	600 %	600 %	
TD: Break	740 %	740 %	
Dart Drop Impact	220 g	220 g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922 ²
MD	370 g	370 g	
TD	630 g	630 g	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Vicat Softening Temperature	223 °F	106 °C	ASTM D1525
Melting Temperature (DSC)	246 °F	119 °C	Dow Method
Optical	Nominal Value (English)	Nominal Value (SI)	Test Method
Gloss	60	60	ASTM D2457
Haze	10 %	10 %	ASTM D1003

Extrusion Notes

Fabrication Conditions For Blown Film:

- Screw Size: 3.5 in.; 30:1 L/D
- Screw Type: DSB II
- Die Gap: 70 mil (1.8 mm)
- Melt Temperature: 418°F
- Output: 12 lb/hr/in. of die circumference
- Die Diameter: 8 in.
- Blow-Up Ratio: 2.5:1
- Screw Speed: 41 rpm
- Frost Line Height: 43 in.

Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

¹ Base density is estimated using the assumption that every 1000 ppm of antiblock in the finished product raises the density of the polymer by 0.0006 g/cm³. Base density is the estimated density of the polymer if it did not contain any antiblock.

² Method B

Product Stewardship

The Dow Chemical Company and its subsidiaries ("Dow") has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Dow products — from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

Medical Applications Policy

NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS: Dow will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:

- long-term or permanent contact with internal bodily fluids or tissues. "Long-term" is contact which exceeds 72 continuous hours;
- use in cardiac prosthetic devices regardless of the length of time involved ("cardiac prosthetic devices" include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass-assisted devices);
- use as a critical component in medical devices that support or sustain human life; or
- use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted. Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.**

Disclaimer

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Dow to change specifications and/or discontinue production; and (4) although Dow may from time to time provide samples of such products, Dow is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

Additional Information

North America		Europe/Middle East	+800-3694-6367
U.S. & Canada:	1-800-441-4369		+31-11567-2626
	1-989-832-1426	Italy:	+800-783-825
Mexico:	+1-800-441-4369		
Latin America		South Africa	+800-99-5078
Argentina:	+54-11-4319-0100		
Brazil:	+55-11-5188-9000		
Colombia:	+57-1-219-6000	Asia Pacific	+800-7776-7776
Mexico:	+52-55-5201-4700		+603-7965-5392

www.dowplastics.com

This document is intended for use within Asia Pacific, Europe, Latin America, North America

Published: 2001-11-05

© 2012 The Dow Chemical Company

