



SMART DEPOT LIMITED

TEL : +886 2 2717 7090 FAX : +886 2 2717 7050 E-Mail : dean@smartbvi.com

CHINA GENERAL PLASTICS CORPORATION PVC RESIN



Grade	K-value	Degree of Polymerization	Bulk Density (g/c.c)	Volatiles (%)	Particles Size (45 mesh pass%)	Foreign matters (grains/100g)	Residual VCM (ppm)
H-58	87~59	700±50	0.52~0.59	≤ 0.3	≥ 99	≤ 40	< 1
H-61	60~62	800±50	0.52~0.59	≤ 0.3	≥ 99	≤ 40	< 1
H-66	65~67	1000±50	0.48~0.56	≤ 0.3	≥ 99	≤ 40	< 1
H-73	72~74	1350±50	0.45~0.53	≤ 0.3	≥ 99	≤ 40	< 1
Test Method	ISO 1628-2	-	ISO 60	ISO 1269	Honeywell SRA-150	Visual Inspection	ISO 6401

Grade	Applications
H-58	Injection Moulding (Fitting), Blowing moulding (Bottle).
H-61	Injection Moulding (Pipe Fitting), Hollow-vacuum Forming (Bottle Blowing), Rigid Film, Shrinkable Film.
H-66	Flexible and Semi-rigid Product For General Purpose (PVC Film, Sheet, Beach Chair, Venetian Blind), Rigid Pipe, Hose, Low Temperature Wire and Cable.
H-73	Hight Impact Flexible Product (PVC leather, Film, Furniture, Shoes), Hight Impact Sheet, Hight Voltage Wire and Cable.